

Technical Data Sheet

- Longkou Excel Chemical

Wax Micro Dispersion PE-3040A

◇ Product Characteristics

This HDPE wax water microdispersion has very low emulsifier content, fast drying, hard, good slipperiness, little effect on the gloss of the coating, and it can effectively improve the surface protection performance and after-tack resistance of water-based coatings.

◇ Application

Application	Function
Print ink, varnish	Abrasion and block resistance
Leather finish	Hand feel, scratch resistance
Water-based wood paint, Water-based plastic paint	Scratch resistance, block resistance, hand feel
Water-based industrial coatings Architectural coatings	
Seed coating agent	Improved flowability, surface protection

◇ Typical Physicochemical Data

Appearance	White liquid
Wax Type	HDPE wax
Emulsion System	Nonionic
Melting Point (°C)	125
Solids (%)	39.0-41.0
Mean Particle Size (μ m)	D50 0.5
pH	9.6-11.6

◇ Storage and transportation

The product is sensitive to temperature and needs to be stored and transported between 5 °C -35 °C . It should be filtered before use. It is recommended to place it in a closed and cool place and pay attention to anti-freezing.

◇ Adding method and processing instruction

It is recommended that wax additives be added at the last stage of the water-based coating processing, added slowly, and stirred while adding. The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible



application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller

disclaims any warranty of merchant ability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product.

Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.